flat glass plate in the range of 0.2 to 0.9, said acrylic resin having a glass transition temperature of 80°C or below.

17. (Amended) A sheet-decorated molding having a surface coated with a decorative sheet formed of an acrylic resin that is a member selected from the group consisting of homopolymers of (meth)acrylates, copolymers containing a (meth)acrylate and mixtures thereof, said acrylic resin containing a lubricant in an amount to give a coefficient of kinetic friction with respect to a flat glass plate in the range of 0.2 to 0.9, said acrylic resin having a glass transition temperature of 80°C or below.

19. (Amended) The sheet-decorated molding of claim 17, wherein said acrylic resin homopolymers and copolymers are selected from the group consisting of polymethyl(meth)acrylate, polyethyl(meth)acrylate, poly-butyl(meth)acrylate, methyl(meth)acrylate-butyl (meth)acrylate copolymers, methyl(meth)acrylate-ethyl(meth)acrylate copolymers, ethyl(meth)acrylate-butyl(meth)acrylate copolymers, and (meth)-acrylate-styrene copolymers.

Please add the following claims:

21. (New) A decorative sheet for use in a sheet-decorating injection molding method, said decorative sheet being formed of an acrylic resin which contains a lubricant in an amount to give a coefficient of kinetic friction with respect to a flat glass plate in a range of 0.2 to 0.9.

22. (New) The decorative sheet according to claim 21, wherein said acrylic resin has a glass transition temperature of 80°C or below.

Still pending need to erase redline